


Product Data Sheet

TRIAMant®

Fly Ash for Concrete according to DIN EN 450



TRIAMant® fly ash is a fine-grained construction material that mainly consists of dust-like, glassy particles. It is produced as a by-product from the process of combustion of hard coal to produce electricity and heat in the power plant “Kraftwerk Trianel Lünen“. Its main constituents are amorphous phases of oxides of silicon, aluminum and iron that are formed in the process from the natural minerals associated with the coal.

Owing to its grain structure and pozzolanic reactivity, fly ash has a positive impact on both fresh concrete and hardened concrete: in green concrete, fly ash improves the workability of concrete; in hardened concrete it increases the compressive strength of the concrete and, by contributing to a denser microstructure of the concrete, also improves the durability of the concrete structure.

TRIAMant® fly ash in accordance with DIN EN 450 can be used as Type II addition in concrete subject to EN 206-1 (national provisions may apply). Fly ash has been used successfully for decades in the concrete producing industry as a high-quality raw material; in designing the concrete composition, the fly ash content may be credited toward the cement content and, via the k-value, towards the water/cement ratio.

The material's high quality is ensured by regular internal quality inspection and monitored by a recognized and independent inspection body. In addition to the Certificate of Conformity issued by MPA NRW, the environmental compatibility of TRIAMant® has been verified in a general technical approval procedure.

Certificates

Certificate of Constasy of Performance:
0432-CPR-00003-01



General technical approval:
Z-3.31-2050

Product Data

based on a statistic evaluation of the product autocontrol results for the year 2017¹⁾

Parameter	Average		Std. dev.	Requirement ²⁾
Normative				
Loss on ignition Category A	2.9	% by mass	0.62	≤ 5.0
Fineness > 0,045 mm Category N	21	% by mass	4.8	20 ± 10
CaO _{total}	4.4	% by mass	0.79	≤ 10.0
CaO _{free}	0.25	% by mass	0.15	- ²⁾
SO ₃	1.0	% by mass	0.23	≤ 3.0
Cl	0.01	% by mass	0.008	≤ 0.10
Na ₂ O _{equiv.}	1.8	% by mass	0.71	≤ 4.0
Particle density	2.36	g/cm ³	0.029	2.30 ± 0.2
Activity index	28d	86	%	≥ 75
	90d	100	%	≥ 85
Informative				
Water demand ³⁾	24.4	% by mass	2.6	-
Bulk density (loose) ⁴⁾	0.90	kg/dm ³	-	-
Bulk density (compacted) ⁴⁾	1.26	kg/dm ³	-	-

- 1) The data compiled in the table shall not be deemed to be warranted characteristics nor constitute any warranty of quality.
- 2) from a content greater than 1.5 % by mass the soundness shall be tested
- 3) for standard consistence to DIN EN 196-3
- 4) result is based on a spot sample